



TDS

Technical Data Sheet

PRIMER/PRIMER SURFACER

58-3016 [Epoxy Primer Green]

1. GENERAL INFORMATION

A Two-component Epoxy Primer that contains epoxy resin as the first part and Polyamide as the second part. It provides excellent adhesion to all metals and protects against harsh conditions that can cause rust on steel surface. In addition, it can be used as heavy build filler without affecting the gloss of top/base coat.

Packing Size : -

2. MIXING

COMPONENTS

58-3016 (Epoxy Primer Green)
21-17 (Hardener for Epoxy Primer)
86-145 (Epoxy Thinner)

MIX RATIO	Volume	By weight	Remark
58-3016	4	5.92	
21-17	1	0.93	
86-145	3	2.70	

APPLY VISCOSITY 14 - 16 second NK#2

POT LIFE 3 - 4 Hour

3. APPLICATION

SURFACE PREPARATION

All surfaces must be thoroughly sanded and cleaned with Concept Wax & Grease Remover prior to application.

-With soap and water. Rinse and wipe dry with clean cloth. Finally, clean surface using Wiping Solvent #85-4 (slow) or #85-7 (fast) with clean cloth.

-Sand steel, aluminum, or galvanized metal with 150 – 240 grit sandpaper. Primer can be applied direct to metal; however, for improved adhesion to metal, we recommend priming with Epoxy Primer #258-xxxx or Etch Primer/Wash Primer #282-xxxx.

-OEM or Original Paint must be cured and sanded with 150 – 240 grit sandpaper. Clear or lacquer must be sanded with 150 – 240 grit sandpaper before to avoid lifting. Body filler or fiberglass must be sanded with 150 – 240 grit sandpaper.

APPLICATION

Number of coats	2 – 3 coats
	Medium wet coats.
	Remark : Mixing ratio, Mixing component and environmental are effect to flash off time.

Dry film thickness 60 - 80

Theoretical Coverages 30 - 35

APPLICATION EQUIPMENT

GUN SET UP*	Compliant	Gravity Feed	1.6 – 2.0 mm
		Siphon Feed	1.6 – 2.0 mm
	HVLP	Gravity Feed	1.8 – 2.0 mm
		Siphon Feed	1.8 – 2.0 mm
AIR PRESSURE*	Compliant	Gravity Feed	20 – 30 psi at the gun
		Siphon Feed	20 – 30 psi at the gun
	HVLP	Gravity Feed	6-8 psi at the cap
		Siphon Feed	6-8 psi at the cap

Remark : Flash time and Dry times will depends on temperature, humidity and wet film thickness.

4.DRY TIME

AIR DRY @25-30 °C

Touch Dry : Contact our Technician
Dry for wet sanding : 180 - 240 minutes
Dry for Dry sanding : 7 - 8 minutes

FORCE DRY at 60-80 °C

Flash off before forcing dry : 5 - 10 minutes
Cycle Time : 30 - 40 minutes
Cool Down : 40 - 60 minutes

INFRARED DRY

Refer to the Infrared Guide for setup recommendations.

Remark : Flash time and Dry times will depends on temperature, humidity and wet film thickness.

5.SANDING

Use 1500 grit wet or finer.

Note: Use caution when sanding or polishing. Cutting too deep into the film may cause a color ring effect.

This can be repaired only by applying the Clear Topcoat over the sanding areas.

6. PHYSICAL PROPERTIES

Specific Gravity : 1.38 - 1.48 g/cm³

Total Non-Volatile Solid : 60 - 70 %

7. VOC REGULATION AREAS

These directions refer to the use of products which may be restrictor require special mixing instruction in VOC REGULATION AREAS. Follow mixing usage and recommendations in the VOC compliant products Chart for your area.

BICBEN®

V. - | Ref. 12172024-35

Issue by Pisarn

Issue date 19/05/2025

