45-8050

Product Data Sheet | ข้อมูลผลิตภัณฑ์



Clearcoat 2K 4:1 Clearguard BIC-BEN[®] 2K 4:1 Topcoat

Version 1 Supply viscosity 20 – 21 Ford cup No. 4 Date 30th October, 2020 Specific gravity 0.85 – 0.95 g/cm³ Shelf life 1 Year Store in average temperature between 40 – 95 °F (5 – 35 °C). Avoid too much

temperature is 70 °F or 21°C

PRODUCT DESCRIPTION

45-LINE is 2K 4:1 polyurethane Topcoat. It's providing adhesion, Good hardness. Excellent in weathering resistance. It's designed for large area.

APPLICATION PARAMETERS

	Part A : Hardener : Thinner			
	4 : 1 : 1 By Volume			
Mixing ratio				
Hardener	21-50 [Infinity 2K DG Hardener] or recommended by our technician			
Reducer Thinner	2K Thinner # 86-120			
Coverage	15 - 20 m ² / liter ready to use mixture at dry film 50 micron			
	By using the recommended application, the theoretical material coverage Note. The practice material usage depends on many factors i.e. shape of object, roughness of the surface, application techniques, pressure and application circumstances.			
Spray viscosity	Ford cup No. 4	15-18 seconds		
Pot life	2– 3 hr. at 25 ^o C			
>1	Gravity feed	1.2 – 1.4 mm		
	Air pressure	1.7 -2.2 bar		
		28 – 30 psi		
Spray condition	HVLP max 0.6 – 0.7 bar (8-10 psi) at			
T	2 coats	Dry film thickness 50-60 micron.		
Number of coats				
} 	10 – 15 mins	at 25 – 30 ^o C		
		20 °C	30 °C	40 °C
(~~)	Dust free time	15 min	7-10 mins	5-10 mins
	Dry to handle	9-10 hr.	7-8 hr.	4-5 hr.
Dry time	Dry to polish	9-10 hr.	7-8 hr.	4-5 hr.
RECAUTION				
k k	For professional or trained app before use, read and follow all reach of children. Always wear product. Apply paint in good ve	TDS, label, and SDS p approved organic var	recautions. Flammab	le product. Keep out

temperature fluctuation or direct contact with sunlight. Suitable storage

KEY CHARACTERISTICS

- 2K 4:1 topcoat
- Good weathering coat