

## Product Data Sheet | ข้อมูลผลิตภัณฑ์



# Clear coat Semi-gloss 2K 2:1 HIGH SOLID BIC-BEN® CLEAR COAT

#### **VERSION**

Version 1
Date 10 January, 2020

#### **PRODUCT DESCRIPTION**

46-8039, Clearcoat Semi-gloss 2K 2:1 High Solid providing semi-gloss, Good hardness. Excellent in weathering resistance. It's design for large area. It's provide long pot life but short time for film setting.

#### **KEY CHARACTERISTICS**

- High solid clearcoat
- Semi-gloss and hardness
- Good weathering clear coat

#### **PHYSICAL PROPERTIES**

Supply viscosity	55 - 65 KU at 30 °C
Specific gravity	1.05 – 1.15 g/cm <sup>3</sup>
Total non-volatile	55 – 65 at 150 °C x 30 mins
Degree of gloss	5 – 15 GU at 60 <sup>0</sup>
Shelf life	1 Year
	Store in average temperature between 40 – 95 °F (5 – 35 °C). Avoid too much
	temperature fluctuation or direct contact with sunlight. Suitable storage
	temperature is 70 °F or 21°C

#### **APPLICATION PARAMETERS**

APPLICATION PARAMETERS			
	Part A : Hardener : Thinner		
	2 : 1 : 5-15% By Volume		
Mixing ratio			
Hardener	2K High Solid Hardener # 21-07		
Reducer Thinner	2K Thinner # 86-120		
Coverage	10 m <sup>2</sup> / liter ready to use mixture at dry film 50 micron		
	By using the recommended application, the theoretical material coverage  Note. The practice material usage depends on many factors i.e. shape of object, roughness of the surface, application techniques, pressure and application circumstances.		
s	Ford cup No. 4 18-20 seconds		
Spray viscosity			
	2– 3 hr. at 25 <sup>o</sup> C		

#### Pot life

<b>&gt;11</b>	Gravity feed	1.2 – 1.4 mm
	Air pressure	1.7 -2.2 bar
		28 – 30 psi
Spray condition		HVLP max $0.6 - 0.7$ bar (8-10 psi) at the air cap
7	2 coats	Dry film thickness 50-60 micron.
Number of coats		
Tash time	10 – 15 mins	at 25 – 30 °C

20 °C

30 min

9-10 hr.

9-10 hr.

30 °C

20 mins

7-8 hr.

7-8 hr.

### PRECAUTION

Warning	For professional or trained applicator use only. Not for sale or use by the general public. before use, read and follow all TDS, label, and SDS precautions. Flammable product. Keep out
	reach of children. Always wear approved organic vapor goggle and safety mask when using product. Apply paint in good ventilating area.

40 °C

10 mins

4-5 hr.

4-5 hr.

Dust free time

Dry to handle

Dry to polish